

Miscellaneous Shapes
Miscellaneous Channels
CAFCO® SprayFilm® WB 3 and WB 4 & ISOLATEK® Type WB 3 and WB 4

ASTM Desig.	Weight	W/D	Metric Desig.	M/D	Hp/A	1-Hour	1-1/2 Hour	2-Hour	3-Hour
MC18 x	58	1.13	460 x 86	66.7	118.6	0.045	0.088	0.139	0.288
	51.9	1.02		x 77	60.2	131.4	0.048	0.095	0.149
	45.8	0.90		x 68	53.1	148.9	0.054	0.106	0.167
	42.7	0.84		x 64	49.6	159.5	0.057	0.113	0.177
MC13 x	50	1.19	330 x 74	70.2	112.6	0.042	0.083	0.131	0.270
	40	0.97		x 60	57.2	138.1	0.050	0.099	0.157
	35	0.86		x 52	50.7	155.8	0.057	0.113	0.177
	31.8	0.78		x 47	46.0	171.8	0.061	0.121	0.191
MC12 x	50	1.28	310 x 74	75.5	104.7	0.038	0.074	0.116	0.241
	45	1.17		x 67	69.0	114.5	0.042	0.083	0.131
	40	1.05		x 60	62.0	127.6	0.048	0.095	0.149
	35	0.92		x 52	54.3	145.6	0.054	0.106	0.167
	31	0.82		x 46	48.4	163.4	0.061	0.121	0.191
	10.6	0.36		x 16	21.2	372.2	0.133	0.263	NR
MC10 x	41.1	1.15	250 x 61	67.9	116.5	0.042	0.083	0.131	0.270
	33.6	0.96		x 50	56.6	139.6	0.050	0.099	0.157
	28.5	0.83		x 42	49.0	161.4	0.061	0.121	0.191
	25	0.77		x 37	45.4	174.0	0.065	0.128	0.201
	22	0.68		x 33	40.1	197.0	0.071	0.130	0.213
	8.4	0.33		x 12	19.5	406.0	0.145	0.266	NR
MC9 x	25.4	0.82	230 x 38	48.4	163.4	0.061	0.121	0.191	0.395
	23.9	0.78		x 36	46.0	171.8	0.061	0.121	0.191
MC8 x	22.8	0.79	200 x 34	46.6	169.6	0.061	0.121	0.191	0.395
	21.4	0.75		x 32	44.3	178.6	0.065	0.128	0.201
	20	0.74		x 30	43.7	181.1	0.065	0.128	0.201
	18.7	0.69		x 28	40.7	194.2	0.071	0.130	0.213
	8.5	0.37		x 13	21.8	362.1	0.133	0.263	NR
MC7 x	22.7	0.83	180 x 34	49.0	161.4	0.061	0.121	0.191	0.395
	19.1	0.72		x 28	42.5	186.1	0.071	0.130	0.213
MC6 x	18	0.72	150 x 27	42.5	186.1	0.071	0.130	0.213	0.453
	16.3	0.71		x 24	41.9	188.7	0.071	0.130	0.213
	15.3	0.61		x 23	36.0	219.6	0.075	0.130	0.213
	15.1	0.66		x 22	38.9	203.0	0.075	0.130	0.213
	12	0.56		x 18	33.0	239.3	0.087	0.172	0.271

Note: All thicknesses are expressed in inches. To convert to Mils, multiply by 1000. To convert to mm, multiply by 25.4